Newtop Chemical Materials (Shanghai) Co.,Ltd. Technical Indicators

NEWTOP

Dabco T catalyst CAS10294-43-5 Evonik Germany

Overview

Dabco T is a tertiary amine-based foaming catalyst that facilitates urea (water-isocyanate) reactions in a variety of hard and soft polyurethane foam applications. It is the industry standard foaming catalyst for soft foams and is used in TDI-based soft foam systems such as mattresses, seats, and automobiles. It is also used in combination with trimer catalysts in PIR laminated paperboard formulations. Dabco T can also be used in MDI, TDI/MDI, MDI High Resilience (HR) soft molding foams as well as self-crusting and microcellular systems. It has a shelf life of 36 months.

NEWTOP 新典化学

CAS No.

Dabco T's CAS number is 10294-43-5. This is a unique identifier for Dabco T that is used to track and identify it throughout the supply chain. CAS numbers are also used to search databases and other resources for information about Dabco T.

Newtop Chemical Materials (Shanghai) Co.,Ltd. Technical Indicators



Physical and chemical properties

The physical and chemical properties of Dabco T are shown in the following table:

Properties	value
Looks	Clear colorless liquid
Scent	A slight ammonia smell
Specific gravity	1.040
Boiling point	200 °C
Flash point	100 °C
Water soluble	Miscible
Solubility in organic solvents	miscibility

Features

Promotes urea (water-isocyanate) reaction

Newtop Chemical Materials (Shanghai) Co.,Ltd.

Technical Indicators

NEUITOP

Used in a variety of hard and soft polyurethane foam applications

Industry standard foaming catalyst for soft foams

For TDI-based soft foam systems, such as mattresses, seats, and automobiles

Use in combination with trimer catalysts in PIR laminated cardboard

formulations

Also available in MDI, TDI/MDI, MDI High Resilience (HR) soft molded foams as

well as self-crusting and microcellular systems

The shelf life is 36 months

Application

Soft polyurethane foam

On-site pouring polyurethane system

PIR laminated cardboard

TDI, TDI/MDI, MDI High Resilience (HR) Soft molded foam

Self-crusting foam

Microcellular foam

Pros

Promotes urea (water-isocyanate) reaction

Newtop Chemical Materials (Shanghai) Co.,Ltd.

Technical Indicators

Used in a variety of hard and soft polyurethane foam applications

Industry standard foaming catalyst for soft foams

Can be used in combination with trimer catalysts

Shelf life is 36 months

Cons

Corrosive to certain metals

Can have a strong odor

Combustible

Similarities and differences with similar products

Dabco T is similar to other tertiary amine-based foaming catalysts in that it promotes

the urea (water-isocyanate) reaction. However, it has a number of advantages over

other products, including its use in a variety of applications, industry standard status

for soft foams, and ability to be combined with trimer catalysts.

Precautions for Use

Wear gloves and safety goggles when handling Dabco T.

Avoid contact with skin and eyes.

Newtop Chemical Materials (Shanghai) Co.,Ltd.

Technical Indicators

Keep away from heat sources and open flames.

Store in a cool, dry place.

Dispose of it properly according to local regulations.

Shelf life:

Remain unopened for two years

Storage and Transportation:

Should be sealed, stored in a dry cool ventilated warehouse

Packing:

200KG/ barrel storage: It is recommended to store in a dry and cool area with proper

ventilation. After the original packaging, please fasten the packaging cover as soon as

possible to prevent moisture and other substances from mixing and affecting the

product performance. Do not inhale dust and avoid contact between skin and mucous

membrane. Smoking, eating and drinking are prohibited in the workplace. Shower and

change after work. Store contaminated clothes separately and use them after washing.

Practice good hygiene.

Technical support and business contacts E-mail: info@newtopchem.com